

# PRODUCTS CHEMICAL

## BIG 10

oil modified urethane gym finish



**THE LATEST IN URETHANE TECHNOLOGY** A clear "hard as nails" gym finish. It is easily repairable. Will penetrate and coat the surface of wood floors and other such surfaces protecting them from abrading, dusting and rubber heel marks.

### RECOMMENDED USES

Excellent finish for gymnasiums, handball and racquetball courts, commercial and decorative floors.



### PRODUCT CHARACTERISTICS

- Approved by Maple Flooring Manufactures Association

### COVERAGE

First Coat . . . . . 300 - 400 sq ft per gallon  
Second Coat . . . . . 400 - 500 sq ft per gallon  
Third Coat . . . . . 500 - 600 sq ft per gallon

Refer to product label and SDS for additional information  
© 2007 Products Chemical Company All rights reserved



## DESCRIPTION

A superior oil modified urethane finish that combines high gloss with tough durability. This product has outstanding leveling characteristics, resistance to yellowing, abrasion, chemicals, and is unsurpassed for resistance to tennis shoe and black heel marks.

## SURFACE PREPARATION

New or sanded floors should be sealed with Big Ten Sealer Ultra and allowed to dry. Screen floor using a 120 or 150 grit screen. Vacuum thoroughly and tack with Waterless Cleaner Floor Prep 2702. Repeat above for second and final coat of finish.

## METHOD OF APPLICATION

1. Apply finish using a lambs wool applicator or T-Bar.
2. Apply finish in thin evenly spread coats.
3. Allow to dry overnight.
4. Screen floor with 100 grit screen if over 24 hours between coats and tack with product No. 2702.
5. Two coats are recommended using above steps.

## DRY TIME

To Touch . . . . . 2 hours  
Hard . . . . . 2-4 hours  
Open to Traffic . . . . . 24 hours  
Between Coats . . . . . 12 - 24 hours

## MFMA SPECIFICATIONS - TEST RESULTS

Clear, no specs or sediment . . . . .	No specs or sediment
Resistant to skinning . . . . .	Resistant
VOC . . . . .	<350 g/l
Set in 1-3 hrs., dry hard in 7 hrs . . . . .	Set 1 hours, Dry hard 2.5 hrs
Tack-free, after 24 hours . . . . .	Tack Free
No loss in dry after 7 days at 125F . . . . .	No Loss
Sward Hardness . . . . .	62
No Wood darkening . . . . .	No Darkening
Damage-free; good adhesion between coats . . . . .	Good Adhesion
Uniform Appearance when patched , . . . . .	Uniform
Resistant to Cold Water . . . . .	Resistant
Resistant to 50% Alcohol . . . . .	Resistant
Resistant to Naphtha . . . . .	Resistant
Resistant to Perspiration . . . . .	Resistant

This product previously met the USDA Standards for use in Federally inspected meat and poultry plants when applicable.

## PRECAUTIONS

Keep out of reach of children. Do not take internally. Keep out of eyes. Avoid prolonged skin contact. Harmful if swallowed. To avoid contamination, do not return used material to original container. Manufacturer will not be responsible for any injury, loss, or damage, if product is used in any manner not in compliance with label direction or if precautions are not observed.

**6400 Herman Avenue  
Cleveland Ohio, 44102  
216.281.1155  
www.prod-chem.com**